



ROIPCT/PTO 03 DEC 2004 #2



INVESTOR IN PEOPLE

The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

PRIORITY DOCUMENT

SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

REC'D 04 DEC 2003


WIPO PCT

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.


Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.



Signed

Dated 5 November 2003

The Patent Office



1/77
12JUN02 E725143-2 D00354
P01/7700 0.00/0213424.5

Request for grant of a patent

(see the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

The Patent Office

Cardiff Road
Newport
Gwent NP9 1RH

1. Your reference PBA/D089134PGB
2. Patent application number 112 JUN 2002
(The Patent Office will fill in this part) 0213424.5
3. Full name, address and postcode of the or of each applicant (underline all surnames)
Patents ADP number (if you know it)

RAISIO CHEMICALS UK LTD
 SETT END ROAD
 SHADSWORTH INDUSTRIAL ESTATE
 BLACKBURN
 LANCASHIRE BB1 2NW
- If the applicant is a corporate body, give the country/state of its incorporation

7457385001
UNITED KINGDOM
4. Title of the invention SIZING
5. Name of your agent (if you have one) Marks & Clerk

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

Patents ADP number (if you know it)

Sussex House
83-85 Mosley Street
Manchester
M2 3LG

18004
6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number

	Country	Priority application number (if you know it)	Date of filing (day/month/year)
7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

	Number of earlier application	Date of filing (day/month/year)
8. Is a statement of Inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:

a) any applicant named in part 3 is not an inventor, or

b) there is an inventor who is not named as an applicant, or

c) any named applicant is a corporate body.

See note (d))

YES

9. Enter the number of sheets for any of the following items you are filing with this form.
Do not count copies of the same document

Continuation sheets of this form

Description

14

Claim(s)

2

Abstract

Drawing(s)

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of Inventorship and right to grant of a patent (*Patents Form 7/77*)

Request for preliminary examination and search (*Patents Form 9/77*)

Request for substantive examination (*Patents Form 10/77*)

Any other documents
(Please specify)

11. I/We request the grant of a patent on the basis of this application.

Signature

Date

MARKS & CLERK

11/06/02

12. Name and daytime telephone number of person to contact in the United Kingdom

MR P.B. ATKINSON – 0161 233 5800

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes


- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

SIZING

The present invention relates to alkenyl succinic anhydride (ASA) and more particularly to its use in the sizing of paper and board.

Paper sizing may be effected using a number of different materials. For example, it is known to effect sizing using a rosin emulsion in conjunction with an aluminium salt (e.g. papermakers' alum) which is effective to cause deposition of the rosin onto the fibres being sized. It is also known to use reactive sizes (e.g. alkyl ketene dimer (AKD) and alkenyl succinic anhydride (ASA), the latter being more reactive than the former.

ASA is normally produced by the reaction of a mixture of long chain alkenes which are such that the olefinic double bond is otherwise than at the α position. The alkene mixture used for this reaction is, in turn, generally obtained by catalytic isomerisation of α -olefins. ASA is a product generally represented by the formula:



where R_1 and R_2 are the same or different alkyl chains.

The reaction of the alkenes with maleic anhydride is conducted with a molar excess of the olefins and is continued until almost zero maleic anhydride content. After the reaction, excess olefin is removed by distillation under reduced pressure (but at pressures which are not low enough to distil the ASA) and is recycled.

For use as a paper sizing agent, the ASA is generally formulated as an emulsion incorporating a stabiliser such as, for example, a starch, a cationic polyacrylamide or other cationic polymer. For use in paper sizing, the emulsion is added to the wet-end of a paper/board making process and may be added to the so-called thick stock (usually comprised of 2% to 5%, e.g. about 3%, by weight of paper making fibres) or to the thin stock (usually comprised of up to 1%, 0.5%, by weight of the fibres). Alternatively the ASA emulsion may be added at the size press.

ASA emulsions are perfectly satisfactory for use in the production of paper and board intended for a wide variety of applications. However they are not currently used (to our knowledge) in the production of so-called "liquid packaging board" which is used for manufacturing cartons and the like for containing liquids, frequently a dairy product such as milk or cream. The liquid packaging board comprises the cellulosic board substrate which is coated on one or both sides thereof with a barrier preventing or inhibiting penetration of the substrate by the liquid to be contained in a carton or the like produced from the board. Frequently the barrier material is of polyethylene but other food grade materials may also be used.

Generally the board is sterilised for use in the production of a septic container. Such sterilisation may be effected after the board has been coated with the barrier material and cut to the required size. The sterilisation is generally effected by means of baths of hydrogen peroxide at elevated temperature. There is however the disadvantage that the hot hydrogen peroxide is able to "infiltrate" the board at its cut edges resulting in undesirable swelling of the fibres from which the board is formed.

It is an object of the present invention to obviate or mitigate the above mentioned disadvantages.

According to a first aspect of the present invention there is provided a paper sizing composition which comprises an aqueous emulsion of an ASA wherein the ASA incorporates a maximum of 1% by weight of polymeric residues.

According to a second aspect of the present invention there is provided a method of producing a sized paper or board wherein the sizing agent is an ASA incorporating a maximum of 1% by weight of polymeric residues.

Sized paper or board produced in accordance with the method of the second aspect of the invention may be used for food grade/catering applications. The board may be used, for example, for cartons intended to contain liquids such as milk, and cream. Alternatively the board may be used for producing paper cups or the like.

We have in fact found that the use of an ASA containing at most 1% of polymeric residues (as opposed to a "conventional" ASA which would normally contain 7-10% of such residues) as a sizing agent provides enhanced resistance to edge penetration by agents such as hot hydrogen peroxide and lactic acid. Thus paper or board which has been sized in accordance with the method of the second aspect of the invention may be provided with a barrier coating, e.g. polyethylene or other food grade material on both surfaces thereof and (after being cut to size if necessary) be sterilised in a bath of hot hydrogen peroxide prior to being converted to cartons of the like, particularly for containing dairy products.

The ASA employed in the present invention preferably contains less than 0.5% by weight of polymeric residues. Furthermore the ASA preferably contains less than 5%, more preferably less than 4% and even more preferably less than 3% by weight of olefins. In particularly preferred embodiments of the invention, the ASA contains less than 1%, more preferably less than 0.5% by weight of olefins.

The ASA employed in the present invention (i.e. one containing a maximum of 1% of polymeric residues) may be an ASA distillate. By the term "ASA distillate" we mean a product that has been obtained by distilling ASA in the sense that the ASA is converted to the vapour phase and subsequently re-condensed to give a distillate. The product to be distilled may be the reaction product of maleic anhydride with a mixture of olefins, most preferably after removal of unreacted olefins. In other words,

the preferred product for distillation is the ASA that is normally used as the material for formulating an ASA sizing composition.

The ASA distillate will generally be obtained by an overall process which involves the steps of:

- (i) reaction of a mixture of olefins with maleic anhydride;
- (ii) removal of excess olefin by distillation under reduced pressure (but at pressures which are not low enough to distill the ASA); and
- (iii) distillation of the product from step (ii) at sufficiently reduced pressure to "distill over" the ASA.

Steps (i) and (ii) are entirely conventional and are the steps used to produce ASA which is then formulated into paper sizing compositions. Thus, for example, a product resulting from steps (i) and (ii) is commercially available under the name RAISAFOB MF.

Distillation of the "crude" ASA to produce the ASA distillate will be conducted at elevated temperature and reduced pressure. Generally the pressure will be a maximum of 100Pa (1 mbar) for which a distillation temperature of 200-210°C is suitable. It is however more preferred that lower pressures are used, most preferably less than 0.5Pa (4×10^{-3} mm Hg). At this pressure, the temperature at which distillation is conducted will generally be 140-160°C.

Distillation may be effected using a wiped film evaporator.

ASA distillates as employed in the present invention will generally contain less than 0.5% by weight of residual polymer content. In contrast the corresponding value for "undistilled" ASA is 7-9% by weight.

If it is desired that the ASA distillate has a low free olefin content then it will generally be necessary to take steps to prevent free olefin being incorporated in the

condensate that is to be used for making the sizing emulsion. For example, when a wiped film evaporator is used for distillation then a volatiles trap may be employed.

ASA distillates have better colour than the "conventional" ASA and may for example have a Gardner colour of about 2 as compared with the value of 4-11 for the undistilled product. Additionally the ASA distillates demonstrate improved size performance (both in terms of Cobb and HST (Hercules Size Test)). These advantages are, of course, additional to those of improved lactic acid resistance and peroxide resistance which have been mentioned earlier.

The ASA distillate may be formulated into a sizing composition, e.g. an emulsion, in exactly the same way as "conventional" ASA. Thus, the ASA distillate may be emulsified in water together with a starch stabiliser. It will generally also be appropriate to use a stabiliser in the formation of the emulsion. Examples of suitable stabilisers are well known in the art and include, for example, starch, ionic starch including cationic and anionic starch, (e.g. potato or waxy maize starch) or a cationic polyacrylamide or other cationic polymer. The amount of stabiliser used is usually up to 25% by weight based on the weight of ASA, more preferably 5% to 20% on the same basis.

Optionally the emulsion will contain at least one surfactant. Examples of suitable surfactants are well known in the art and include, for example, phosphate, esters, phosphate ethers, nonyl phenol ethoxylates, polyacrylamides, and lignosulphonic acid derivatives. The amount of surfactant used is generally up to 5% by weight of ASA.

If desired, a metal cation may be incorporated with the ASA to be emulsified to provide an emulsion having a coating of an insoluble salt of alkenyl succinic acid in accordance with the teachings of WO-A-00 20686 (Raisio).

The emulsion in accordance with the invention may be used in an entirely conventional means for sizing of fibres to be used for the formation of paper, board

and like material. For this purpose, the emulsion will be added to the wet-end of a paper making process and may be added to the so-called thick stock (usually comprised of 2% to 5%, e.g. about 3%, by weight of the papermaking fibres) or to the thin stock (usually comprised of up to 1%, e.g. about 0.5% by weight of the papermaking fibres). Alternatively the ASA emulsion may be added at the size press.

The invention will now be further described with reference to the following Examples.

Examples

The Example illustrates distillations of a batch of Raisafob MF (Batch A) for which an analysis of Olefin and polymeric residue content is given in Table 1 below together with the same analysis for other batches of Raisafob for the purposes of comparison.

1. ASA Distillation

(i) Laboratory Distillation (small scale)

A conventional vacuum distillation system was used. Approximately 200ml Raisafob MF (Batch A) were introduced into a 500 ml round bottomed flask filled with a distillation head and a simple air condenser. The flask was heated in an oil bath. The temperature and pressure conditions were 200-210 °C and 100Pa (1.0 mbar). The first fraction, containing approximately 5% unreacted olefin was discarded.

(ii) Plant Distillation (production scale)

A Wiped Film Evaporator was used to distil 2 tonnes of Raisafob MF (Batch A).

The wiped film evaporator was operated at 150-200 kilos per hour in two stages. The first was a degassing stage using a pressure of 2×10^{-1} mbar and a temperature of 150°C . The second stage used a pressure of 4×10^{-2} mbar and a temperature of 165°C .

The properties of the resultant distillates are shown in Table 1.

TABLE 1

No	ASA	Olefin content (%)			Viscosity (mPas)	Polymeric residue (%)	Colour (Gardner)
		C ₁₆	C ₁₈	Total			
1	Raisafob MF (Batch A)	0.24	1.92	2.16	170	7.24	6-7
2	Raisafob MF (Batch B)	0.78	3.74	4.52	-	7.52	4
3	Raisafob MF (Batch C)	0.63	2.48	3.11	-	7.38	5-6
4	Raisafob MF (Batch D)				212	9.54	10-11
5	Distilled Raisafob MF (Plant distillation)	0.10	3.46	3.56	110	0.4	2
6	Distilled Raisafob MF (lab distillation)	0.16	0.03	0.19	-	0	2

For the plant distilled ASA the first distilled fraction (containing a significant proportion of unreacted olefin) was not discarded as it was for the laboratory distilled ASA. Therefore, although the percentage of C₁₆ olefin has been reduced, largely the olefin percentage of the ASA has not been affected.

2. Preparation of Emulsions of ASA and Hydrolysis Studies

Small scale emulsions for laboratory study were prepared containing 5% ASA and 0.95% Hicat 158 (cationic starch ex Roquette). Rates of hydrolysis of the resultant emulsions were measured by Fourier Transform Infra-Red spectroscopy and the results are shown in Table 2.

TABLE 2

Temperature °C	ASA Remaining after 8 hours (%)	
	Undistilled	Distilled*
30	81	90
40	38	48
50	0	4

* Distilled following the laboratory procedure.

The emulsion prepared with distilled ASA thus has a lower rate of hydrolysis when compared to its non-distilled counterpart.

3. Pilot Paper Machine Trial

Pilot Machine

Paper was produced on a pilot papermaking machine which had a Fourdrinier forming section with foils, table rolls, vacuum boxes, couch rolls and dandy roll. It contained an open headbox with slices.

The first press has a maximum nip pressure of 25 kg cm⁻¹. The second press has a plain reverse press having a maximum nip pressure of 25 kg cm⁻¹.

The pre-dying section includes 7 steam heated, temperature controlled cylinders with a maximum temperature of 130°C. The pilot machine was equipped with a horizontal size press. The after dryer section consisted of 3 heated cylinders with a maximum temperature of 130°C.

The pilot machine was equipped with a horizontal size press. The after dryer section consists 3 heated cylinders with a maximum temperature of 130°C. The

machine calendar contained 5 nips, steam heated chilled steel rolls, with a maximum temperature of 130°C. The machine calendar contained 5 nips, steam heated chilled steel rolls, with a maximum temperature of 100°C.

The pilot machine had 1 Machine chest of 2000 litres capacity and 4 Stock holding chests of 1000 litres capacity.

The machine incorporated two tubes, separated by 1 cm, placed in the accept side of the mixing box. One tube was used for ASA emulsified with Raisamyl addition and one tube was used for starch Amylofax addition. A tube for filler addition was connected to the tube delivering dilution water to the mixing box.

Materials

Material	Nature / Source
ASA Emulsion	ASA emulsions (1%) were prepared using a Moulinex ® type 530 food blender by emulsifying together a 1:1 ratio of ASA:Riasamyl 135 (starch). The emulsification period for all emulsions was 5 minutes.
ASA	Raisafob MF (undistilled) and Distilled Raisafob MF (Laboratory distillation)
Cationic wet end starch	Hydroxypropyltrimethylammonium ether of potato starch (available as Amylofax 75 (Avebe))
Pigment	Calcium Carbonate, used as an aqueous dispersion of natural ground calcium carbonate. Weight specification 69 ± 2 %. The product contained 100-200 PPM biocide and 0.15-0.5% auxiliary agent (dispersant) (available as Hydrocarb 89 ME, (Omya Croxton Garry))
Polyaluminium chloride solution	Pax 10% (Tan International Ltd)

Optical brightening agent	Tinopal ABP-Z (Ciba Speciality Chemicals PLC)
Pulp and water for a UK papermill.	4 tonnes taken after the refiner 2 tonnes broke 10 tonnes of dilution water

Machine Conditions (Reference Conditions (wet end))

The machine was operated under the conditions set out below and also using an addition level of 0.17% ASA on paper weight. One paper (Reel No. 1A) was manufactured using the ASA emulsion produced with the ASA distillate (Laboratory scale) and the other (Reel No. 12) was manufactured with the ASA emulsion produced from Raisafob MF.

Component	Amount
Starch	4 kg tonne ⁻¹
PAC, to wire tray	1 kg tonne ⁻¹
Tinopal ABP-Z-LIQ to machine chest	5.9 litres tonne ⁻¹
pH	not adjusted
Water circuit	As closed as possible

Paper

Property	Quantity
Bulk / m ³ kg ⁻¹	1.3 (Target 1.3)
Grammage / gsm	84 (Target 80)
Base sheet weight / gsm	66 (Target 66)
Sheet weight after filler addition	84 (Target 80)

4. Paper Testing from Machine Trial

The papers of Reel Nos. 1A (Invention) and 12 (Comparative) were tested

- (a) in the Hercules Size Test (HST) which measures the time in seconds to achieve a fixed level of penetration (i.e. high values = good sizing); and

(b) for Peroxide and Lactic Acid Resistance (Raw Edge) Penetration (REP)) using the procedure described in Appendix 1.

The results were as follows:

Reel No.	Fifth day Natural Cobb	Fifth Day Natural HST	Lactic Acid Resistant		Peroxide Resistance/kg m ⁻²
			1 Hour / kg m ⁻²	24 Hours/kg m ⁻²	
1A	17.7	167	1.1	3.19	8.41
12	17.3	264.2	0.79	2.72	4.13

Summary and Conclusions

Distilled ASA and paper board produced using an emulsion which comprises distilled ASA show the following advantages over their non-distilled counterparts.

1. Much better colour (Gardner of ~2 compared with 4-11)
2. Much lower residual polymer content (<0.4% compared with 7-9%)
3. Much lower residual olefin content (if first fraction is discarded as the case of laboratory distillation) (<0.2% compared with 2-5%)
4. Better hydrolytic stability (10% hydrolysed in 8 hours at 30°C compared with 20%)
5. Better Sizing performance (HST of 264 seconds compared with 167 sec)
6. Better lactic acid resistance (0.8 kg/m² after 1 hour compared with 1.1 kg/m²)
7. Better Peroxide resistance (4.13 kg/m² compared with 8.41 kg/m²)

APPENDIX 1

Sizing Test methods

Cobb and Hercules Size Test (HST)

Both Cobb and HST tests measure aqueous penetration through the XY plane.

The Cobb test measured the amount of water penetration in g/m^2 after exposing the XY plane to liquid water. The lower the Cobb value the lesser the penetration by water and hence the better the sizing of the paper.

The HST measures the time in seconds to achieve a fixed level of penetration. The higher the HST value the slower the penetration and hence the better the sizing of the paper.

Lactic Acid and Peroxide Resistance – Raw Edge Penetration (REP)

Sample Preparation

Samples of liquid packaging board were conditioned for 24 h at 23 °C in a humidity of 50 %. The thickness of the conditioned board was measured and the sample was cut to a piece sized 10x30 cm (with the shorter side (10 cm) in the machine direction). The sample was masked on both sides cut into pieces sized 2.5x7.5 cm (with the shorter side (2.5 cm) in the machine direction), and thereafter weighed.

Lactic acid REP

The weighed sample was placed in a basin, containing 1 % lactic acid, for 24 h at room temperature. The surface was dried with absorbent boards and the sample was weighed promptly.

Peroxide REP

A lidded glass basin, containing 30 % hydrogen peroxide, was heated to 70 °C. The sample was placed into the basin for 10 minutes. The surface was dried with absorbent boards and weighed promptly.

REP Calculation

The REP is calculated using the following formula:

$$\text{REP (g/mm}^2\text{)} = A/a \times L$$

where A = the weighing difference of the sample before and after treatment,
g

a = thickness, mm

L = the perimeter of the sample, mm

For each sample 5 pieces were tested.

The lower the REP value the slower the penetration and hence the better the sizing of the paper.

CLAIMS

1. A paper sizing composition which comprises an aqueous emulsion of an ASA wherein the ASA incorporates a maximum of 1% by weight of polymeric residues.
2. A composition as claimed in claim 1 wherein the ASA incorporates a maximum of 0.5% by weight of polymeric residues.
3. A composition as claimed in claim 1 or 2 wherein the ASA contains less than 5% by weight of olefins.
4. A composition as claimed in claim 3 wherein the ASA incorporates less than 0.5% by weight of olefins.
5. A method of producing a sized paper or board wherein the sizing agent is an ASA incorporating a maximum of 1% by weight of polymeric residues.
6. A method as claimed in claim 5 wherein the ASA incorporates a maximum of 0.5% by weight of polymeric residues.
7. A method as claimed in claim 5 or 6 wherein the ASA contains less than 5% by weight of olefins.
8. A method as claimed in claim 7 wherein the ASA incorporates less than 0.5% by weight of olefins.
9. A method as claimed in claim 5 wherein the sizing agent is provided by a paper sizing composition as claimed in any one of claims 1 to 4.
10. Sized paper or board produced by the method of any one of claims 5 to 9.

11. Sized paper of board as claimed in claim 10 provided on both surfaces thereof with a barrier coating of a food grade material.

12. A method of producing a carton comprising sterilising paper or sized board as claimed in claim 10 with hot hydrogen peroxide and converting the sterilised paper or board to a carton.

PCT/GB2003/002534

